

ZHANJIANG KINGSTAR BUILDING MATERIAL CO., LTD.  
2/F, BUILDING A, ZIWEI GARDEN, NO.41 HAIBIN ROAD 3, ZHANJIANG, GUANGDONG, CHINA

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description : WPC FOAM SHEET  
 Color : WOOD COLOR  
 Thickness : 19mm  
 Composition : PVC RESIN + WOOD POWDER + ADDITIVES  
 Density : 0.60g/cm<sup>3</sup>  
 Sample Receiving Date : Apr.23, 2019  
 Test Performing Date : Apr.23, 2019 to May 06, 2019

**Test Result Summary**

No.	Test(s) Requested	Result(s)	Comments
1	ASTM E84-18b Standard Test Method for Surface Burning Characteristics of Building Materials	Does not meet class C	/
For further details, please refer to the following page(s)			

Signed for and on behalf of  
Shunde Branch  
SGS-CSTC Co., Ltd.



Ivette Zhang  
Approved signatory



SGS-CSTC Standards Technical Services Co., Ltd.  
Shunde Branch Harbin

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

11F, 1<sup>st</sup> Building, European Industrial Park, No.1 Shunhe South Road, Wusha Section, Daliang Town, Shunde, Foshan, Guangdong, China 528333 t (86-757)22805888 f (86-757)22805858 www.sgs.com.cn  
 中国·广东·佛山市顺德区大良街道办事处五沙顺和南路1号欧洲工业园一号厂房首层 邮编: 528333 t (86-757)22805888 f (86-757)22805858 e sgs.china@sgs.com

**Test Conducted:**

This test was conducted in accordance with ASTM E84-18b Standard Test Method for Surface Burning Characteristics of Building Materials

**Introduction:**

The method, designated as ASTM E84-18b, "Standard Method of Test for Surface Burning Characteristics of Building Materials", is designed to determine the relative surface burning characteristics of materials under specific test conditions. Results are expressed in terms of flame spread index (FSI) and smoke developed index (SDI).

The purpose of this test method is to determine the relative burning behavior of the material by observing the flame spread along the specimen. Flame spread and smoke developed index are reported. However, there is not necessarily a relationship between these two measurements.

**Test Procedure:**

The tunnel is preheated to 150°F, as measured by the floor-embedded thermocouple located 23.25 feet downstream of the burner ports, and allowed to cool to 105°F, as measured by the floor-embedded thermocouple located 13 feet from the burners. At this time the tunnel lid is raised and the test sample is placed along the ledges of the tunnel so as to form a continuous ceiling 24 feet long, 12 inches above the floor. The lid is then lowered into place.

Upon ignition of the gas burners, the flame spread distance is observed and recorded every 15 seconds. Flame spread distance versus time is plotted ignoring any flame front recessions. If the area under the curve (A) is less than or equal to 97.5 min·ft, FSI = 0.515·A; if greater, FSI = 4900/(195-A). Smoke developed is determined by comparing the area under the obscuration curve for the test sample to that of inorganic reinforced cement board and red oak, arbitrarily established as 0 and 100, respectively.

**Sample Description:**

Thickness	:	Approximately 19mm
Exposed face	:	One face

**Sample Preparation:**

Prior to testing, the specimen was conditioned to constant weight at a temperature of (73.4± 5)°F (23 ± 2.8)°C and a relative humidity of (50 ± 5)%.

The test specimen consisted of a total of 11 sections of material. The sections were butted together during testing to form the requisite specimen length. The specimen was self-supporting on the ledges of the test chamber.



**Test Results:**

**Test data and observations:**

Ignition time:	22 seconds.
Maximum flame spread (ft):	7.5
Time To Maximum Spread:	371 seconds.
Observations of the burning characteristics	Fall out
Test Duration:	10 minutes.
FS*Time area (ft*min):	60.4
Smoke area (%A*min):	690.4
Red oak smoke area (%A*min):	90.8

**Summary of results:**

Flame-spread Index (FSI)	Smoke-developed Index (SDI)
30	750

**Rating:**

The National Fire Protection Association Life Safety Code 101, "Interior Wall and Ceiling Finish Classification", has a means of classifying materials with respect to Flame Spread and Smoke Developed when tested in accordance with NFPA 255, (ASTM E84) "Method of Test of Surface Burning Characteristics of Building Materials". The classifications are as follows:

	<u>Flame-Spread Index (FSI)</u>	<u>Smoke-developed Index(SDI)</u>
Class A	0 - 25	0 - 450
Class B	26 - 75	0 - 450
Class C	76 - 200	0 - 450

**Conclusion:**


Refer to the National Fire Protection Association Life Safety Code 101, "Interior Wall and Ceiling Finish Classification", the submitted sample does not meet the requirement of Class C.




Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com**

### Appendix 1-Graphs:





**Graph1. Flame Spread Index**



**Graph2. Smoke Developed Index**



### Appendix 2-Pictures:



\*\*\*End of Report\*\*\*

